



GRASSELLO

TECHNICAL DATA SHEET N°58

TRANSPIRING LIME BASED PRODUCT FOR INTERNAL AND EXTERNAL SURFACES.

CHARACTERISTICS: “GRASSELLO” is a product formulated with sasond pure lime, mineral extenders, non-organic pigments, binders, bactericide which provide the product with the following characteristics:

- excellent transirability;
- Washability and minimum dirt retention (internal surfaces);
- Easy application and bright finish.

“GRASSELLO DI CALCE” for internal surfaces is suitable for decorating walls, plaster strips, columns, ceilings.

“GRASSELLO DI CALCE” for external surfaces is suitable for decorating surfaces treated with a previous layer of cement or lime.

SUPPORT PREPARATION: *On chalking surfaces:* apply a coat of “IMPREGNANTE ACRILICO” diluted with 1:1 water. Old paints should be removed where flaking or not very adherent. Old plaster layers that are no longer in a good condition can be renovated with the application of mortat in the damaged areas.

APPLICATION: Remix the product and apply it on a previously wetted surface using a stainless steel tool. Apply two coats of product with an interval of 4/6 hours between the coats. With the same tool, proceed with the final layer pressing the tool on the wall, up to obtain a smooth surface.

WARNINGS: Do not apply the product at temperatures below + 6° C. Wet the surface before the application.

SPECIFIC WEIGHT: kg/lt. 1.45 ± 0.05 at 23 ±2°C

COVERAGE: 1.5 – 2 kg per squared meter on a flat and well-smoothed surface

RESISTANCE TO DIFFUSION OF STEAM: 18 mic.;

TEMPERATURE FOR CARBONATION: + 10° C;

FINAL ASPECT: Bright without wax;

COLOURS: White. Other colours as reported on “Teate” colour display brochure.

PACKAGES: 2.5 – 5 – 14 lt. buckets.

TOOL MANTEINANCE: Wash immediately after use with water.



Colorificio ARCO S.p.a.
Via Adige, 1 (Zona Industriale) - 66020 S. Giovanni Teatino (CH)
Tel. 085.44.62.232 (r.a.) - Fax 085.44.61.803



STORAGE:

Keep in a cool dry place far from frost. In sealed buckets, the product remains in its original state for 24 months.